



The
Patent
Office

PCT/GB 98 / 0 2 5 2 6

REG'D 1 5 SEP 1998
The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP9 1RH
PCT
09/508322

PRIORITY DOCUMENT

09/508322

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Andrew Gersey

Dated


3 September 1998

BEST AVAILABLE COPY

RECEIVED

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



SEP97 E301242-1 D01975
901/7700 25.00 - 9718982.3

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference

TNT 2621

2. Patent application number
(The Patent Office will fill in)

9718982.3

09 SEP 1997

3. Full name, address and postcode of the or of each applicant (underline all surnames)

T&N TECHNOLOGY LIMITED
CAWSTON HOUSE
CAWSTON LANE
RUGBY, WARWICKSHIRE
CV22 7SA

Patents ADP number (if you know it)

755231001 ✓

If the applicant is a corporate body, give the country/state of its incorporation

ENGLAND

4. Title of the invention

DISC BRAKE ROTOR

5. Name of your agent (if you have one)

P L DRURY, J A CRUX, G K GIBSON,
J HAMMERSLEY, J A MOFFAT
T&N PLC
BOWDON HOUSE
ASHBURTON ROAD WEST
TRAFFORD PARK
MANCHESTER
M17 1RA

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Patents ADP number (if you know it)

5943790001 ✓

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or

c) any named applicant is a corporate body.

See note (d))

Patents Form 1/77

9. Enter the number of sheets of any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form ☐

Description ☒

Claim(s) ☒ 2

Abstract ☒ 1

Drawing(s) ☐

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(please specify)

11.

I/We request the grant of a patent on the basis of this application.

Andrey
Signature

Date 5. Sept 1997

DR A R BEGG, DIRECTOR, T&N TECHNOLOGY LIMITED

12. Name and daytime telephone number of person to contact in the United Kingdom

P L DRURY - 01788 528356

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

This invention is concerned with a disc brake rotor.

A disc brake rotor is arranged to rotate with a member, such as a wheel of a vehicle or a rotating part of a machine. Such a rotor provides two oppositely-facing annular friction surfaces which, in the operation of the brake, are engaged by blocks of friction material to decelerate the rotor and hence the member. Two of the friction material blocks are moved (usually by hydraulic means) towards one another into contact with the two friction surfaces so that frictional forces occur slowing the rotation of said rotor, and hence of said member.

In selecting a material for a disc brake rotor, it is necessary to consider the coefficient of friction of the material and its thermal properties, since considerable heat is generated during braking. Conventionally, disc brake rotors for passenger vehicles have been made from unalloyed grey irons consisting of flake graphite in a pearlitic matrix. These have carbon contents in the range 3.25-3.55 wt% and strength levels are typically approximately 220 MPa. In order to increase thermal conductivity, the carbon level can be increased to 3.65-3.95 wt% but this decreases the strength, eg to approximately 150 MPa. Increased carbon levels also may result in microstructural defects so that casting difficulties are increased.

It is well known to alloy the higher carbon-containing irons with matrix strengthening elements such as chromium, molybdenum, nickel and vanadium in order to increase the strength. For example, WO 96/07766 discloses a pearlitic grey iron which comprises 3.5-3.7 wt% carbon, 1.9-2.05 wt% silicon, 0.05-0.1 wt% vanadium, 0.2-0.3 wt% molybdenum, 0.2-0.3 wt% chromium and 0.2-0.3 wt% copper. EP 0778355 A discloses a grey cast iron for brake discs containing 3.65-3.95 wt% carbon, 1.8-2.2 wt% silicon, 0.2-0.4 wt% chromium,

0.2-0.8 wt% niobium and 0.3-0.5 wt% copper. However, alloying has a detrimental effect on thermal conductivity.

In addition to thermal and mechanical considerations, a material for a disc brake rotor must exhibit good wear resistance. In an unalloyed iron, wear resistance is primarily a function of the matrix structure and its hardness. Alloying the iron can create carbides so that wear resistance becomes more a function of the properties of the carbides. However, when vanadium, titanium and chromium are added to iron in excess quantities, a fall in the strength occurs arising from the formation of intergranular carbides in the matrix. Carbide stabilising elements such as chromium, molybdenum and vanadium also increase the tendency for the formation of free ferrite which is detrimental to the strength and tribological properties. For this reason, these elements are normally used at levels which are below those at which free carbides are formed so that the wear benefits of free carbides are not obtained. It is also considered that the use of high alloy structures containing free carbides would cause the formation of "hot spots" resulting in brake judder and heat cracking.

The present invention has the object of further increasing the thermal fatigue and wear resistance properties of a disc brake rotor.

The invention provides a disc brake rotor having a grey cast iron composition, wherein said composition comprises between 0.5 and 1.2% by weight of copper, and one or more hard carbide forming metals, the ratio between the weight of copper present and the weight of said one or more hard carbide forming metals being 1.8 to 3 units of copper to 1 unit of the one or more hard carbide forming metals.

In a disc brake rotor according to the invention improved thermal fatigue and wear resistance properties are achieved by a careful balance of the additives which, on the one hand, avoids a detrimental microstructure with inter-granular carbide eutectic phases and, on the other hand, gives higher wear resistance. The hard carbide forming metals can be selected from vanadium, tungsten, chromium, molybdenum, titanium, and niobium.

It has previously been recognised that titanium levels can have a critical effect on the co-efficient of friction and wear characteristics of a cast iron disc brake rotor. Levels below 0.1 wt% promote "graphitisation" and form hard discrete particles of titanium carbonitride. Such particles dramatically increase wear performance but, above 0.05 wt% of titanium, the rotors become difficult to machine, bedding-in of the rotor is very slow, and the friction material wear is increased. In order to avoid these problems, preferably, in a disc brake rotor according to the invention, the composition comprises both vanadium and titanium with the weight of vanadium present being less than or equal to one half of the weight of copper present added to 20 times the weight of titanium present. By this careful selection of titanium, vanadium and copper improved wear and frictional properties can be achieved without the problems of hot-spotting and manufacturing difficulties.

Preferably, in a disc brake rotor according to the invention, the carbon equivalent of the composition is between 4.2 and 4.47, the titanium content of the composition is between 0.025 and 0.035 wt%, the vanadium content of the composition is between 0.35 and 0.45 wt%, and the copper content of the composition is between 0.7 and 0.9 wt%.

There now follow detailed descriptions of two disc brake rotors which are illustrative of the invention.

The first illustrative disc brake rotor has a grey cast iron composition. In order to form the first illustrative disc brake rotor a base cast iron composition was alloyed. The base iron composition was as follows:

carbon 3.65 wt%, silicon 2.10 wt%, phosphorus 0.06 maximum, manganese 0.65 wt%, sulphur 0.10 wt%, nickel residual, and the balance iron. This gave a carbon equivalent of 4.2 to 4.37.

It is considered that practical limits for the base grey iron are:

carbon 3.5-3.7, silicon 2.00-2.20, phosphorus 0.10 maximum, manganese 0.60-0.80, and sulphur 0.15 maximum.

To the base composition, alloying materials were added to give a vanadium content of 0.35 wt%, a titanium content of 0.025 wt%, a chromium content of 0.05 wt% maximum, and a copper content of 0.8 wt%. It should be noted that the composition comprises hard carbide forming metals (vanadium and titanium) which at 0.375 wt% is less than half of the copper content at 0.8 wt%. Thus, the ratio between the weight of copper present and the weight of the hard carbide forming metal is 2.13 units of copper to 1 unit of the hard carbide forming metal.

It should also be noted that the vanadium and titanium present satisfies the formula that the weight of the vanadium present (0.35 wt%) is less than one half of the weight of the copper present added to 20 times the weight of titanium present (0.8 wt% of copper divided by 2 gives 0.4 wt% plus 20 times 0.025 wt% equals 0.9wt%).

The first illustrative rotor was compared in wear tests with a comparison rotor made of a conventional base grey cast iron used for disc brake rotors. This cast iron has a composition of:

carbon 3.42 wt%, silicon 2.37 wt%, manganese 0.65 wt%, sulphur 0.09 wt%, phosphorus 0.04 wt%, chromium 0.3 wt%, titanium 0.03 wt% and the balance iron.

In a wear test at low pressure, the wear on the first illustrative rotor was 69% of that of the comparison rotor. In a medium pressure wear test, the wear on the first illustrative rotor was 57% of that of the comparison rotor. In a high pressure wear test, the wear on the first illustrative rotor was 71% of that of the comparison rotor. In the same tests, the wear on the friction material pads running against the first illustrative rotor was 79%, 88%, and 89%, respectively, compared to the wear on the friction material pads running against the comparison rotor.

The first illustrative rotor was also compared with the comparison rotor in a thermal fatigue resistance test, ie a test in which the materials were stressed cyclically to pre-determined stress levels at various temperatures and the number of cycles to failure were measured. The first illustrative rotor consistently achieved superior results to the comparison rotor, eg at 250°C, at a stress level of 75 MPa the comparison rotor failed at 18,000 cycles whereas the first illustrative rotor failed at 282,000 cycles, and, at a stress level of 70 MPa, the comparison rotor failed at 63,000 cycles whereas the first illustrative rotor failed at 1,122,000 cycles.

The second illustrative disc brake rotor has a grey cast iron composition. Said composition is 3.53 wt% carbon, 2.04 wt% silicon, 0.63 wt% manganese, 0.1 wt% sulphur, 0.06 wt% phosphorus, 0.29 wt% chromium, 0.79 wt% copper, 0.011 wt% titanium, 0.10 wt% vanadium, and the balance iron. Thus, the hard carbide forming metals (chromium, titanium and vanadium total 0.401 wt% so that the ratio between the weight of copper present and the

weight of said hard carbide forming metals is 1.97 units of copper to 1 unit of the hard carbide forming metals.

The second illustrative rotor was compared in wear tests with a comparison rotor made of a conventional base grey cast iron described above. In a medium pressure wear test, the wear on the second illustrative rotor was 79% of that of the comparison rotor, and the wear on the friction material pads was 84% of that of the pads running against the comparison rotor.

CLAIMS

- 1 A disc brake rotor having a grey cast iron composition, wherein said composition comprises between 0.5 and 1.2% by weight of copper, and one or more hard carbide forming metals, the ratio between the weight of copper present and the weight of said one or more hard carbide forming metals being 1.8 to 3 units of copper to 1 unit of the one or more hard carbide forming metals.

- 2 A disc brake rotor according to claim 1, wherein the hard carbide forming metals are selected from vanadium, tungsten, molybdenum, chromium, titanium, and niobium.
- 3 A disc brake rotor according to either one of claims 1 and 2, wherein the composition comprises both vanadium and titanium with the weight of vanadium present being less than or equal to one half of the weight of copper present added to 20 times the weight of titanium present.
- 4 A disc brake rotor according to any one of claims 1 to 3, wherein the carbon equivalent of the composition is between 4.2 and 4.47.
- 5 A disc brake rotor according to any one of claims 1 to 4, wherein the titanium content of the composition is between 0.025 and 0.035 wt%.
- 6 A disc brake rotor according to any one of claims 1 to 5, wherein the vanadium content of the composition is between 0.35 and 0.45 wt%.

- 7 A disc brake rotor according to any one of claims 1 to 6, wherein the copper content of the composition is between 0.7 and 0.9 wt%.
- 8 A disc brake rotor substantially as hereinbefore described with reference to the first or the second illustrative rotor..
-

ABSTRACTDisc Brake Rotor

A disc brake rotor having a grey cast iron composition.

Said composition comprises between 0.5 and 1.2% by weight of copper, and one or more hard carbide forming metals, the ratio between the weight of copper present and the weight of said one or more hard carbide forming metals being 1.8 to 3 units of copper to 1 unit of the one or more hard carbide forming metals.

PCT/GB98/02526

21.8.98

T & N

9718982.3

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- ✓ • FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

This Page Blank (uspto)